

FICHA TÉCNICA: CAPUCHONES CONTRACCIÓN EN FRIO



REFERENCIA: CCF

- Material: EPDM Rubber.
- Resistente al agua.
- Resistente a los ácidos.
- Resistente rayos ultravioletas



Property	Test method	Value
300% Modulus	ASTM D412-75	4,2 Mpa
Ultimate tensile	ASTM D412-75	10.05Mpa
Ultimate Elongation	ASTM D412-75	600%
Tear strength	ASTM D2671	1.10~1.20
Low temperature flexibility(40°C/4h)	ASTM D624C-73	28,3KN/m
Fugus resistance	ASTM G-21	28dyas, no growth
Halogen free	IEC 61249-2-21	CI 900 ppm max Br 900ppm max. Total Cl+Br 1500ppm max
Moisture Absortion 7 days 90°C in H2O		3,0% wt. Gain